



ELEKTRON® EQ21

ELEKTRON EQ21 is a high strength magnesium casting alloy developed by Magnesium Elektron to have good ambient and elevated temperature properties whilst still retaining good foundry characteristics.

It is a fully heat treatable magnesium alloy containing silver and rare earth metals. It is pressure tight, weldable and may be used up to temperatures of 200°C.

ELEKTRON EQ21 may be used to replace ELEKTRON MSR-B with a cost saving since the silver content is reduced to 1.3%-1.7% compared with 2.0% - 3.0% in ELEKTRON MSR-B. The lower silver content reduces the cost of the basic metal content in castings and improves the price stability.

APPLICATIONS

The alloys will be of interest to designers requiring good retention of properties at elevated temperatures for aerospace, automotive and military applications.

SPECIFICATIONS

AECMA MG-C64001

AMS 4417

ASTM B80 EQ21A-T6

BS 2970 MAG 13-TF

UNS M18330

ISO 16220 MC65220

CHEMICAL COMPOSITION

Silver	1.3-1.7%
Rare Earths	1.5-3.0%
Copper	0.05-0.10%
Zirconium	0.4-1.0%
Magnesium Balance	

HEAT TREATMENT

The alloy is used in the T6 heat treated condition ie: 8 hours at 520°C, hot water or polymer quench, age for 16 hours at 200°C.

PHYSICAL PROPERTIES

Specific gravity	1.81
Coefficient of thermal expansion	$26.7 \times 10^{-6} \text{K}^{-1}$
Thermal conductivity	$113 \text{Wm}^{-1}\text{K}^{-1}$
Specific heat	$1000 \text{Jkg}^{-1}\text{K}^{-1}$
Electrical resistivity	68.5 nΩm
Modulus of elasticity	44 GPa
Poissons ratio	0.3
Melting range	540-640°C
Damping Index	0.22
Vickers hardness	80-105

DESIGN DATA

Minimum specification tensile properties
BS 2970 MAG13-TF

0.2% Proof stress	175 MPa
Tensile strength	240 MPa
Elongation	2% HEAT TREATMENT

The alloy is used in the T6 heat treated condition ie: 8 hours at 520°C, hot water or polymer quench, age for 16 hours at 200°C.

OTHER PROPERTIES

CASTABILITY

Fine grained and pressure tight with good casting characteristics.

PATTERN MAKERS SHRINKAGE FACTOR

1.3%

WELDABILITY

Weldable by the tungsten arc inert gas process (TIG) with a filler rod of a similar composition. Castings should be welded in the T4 or T6 condition and given the following post weld heat treatment:

1 hour at 505°C,
quench,
followed by 16 hours at 200°C.

MACHINING

ELEKTRON EQ21 castings, like all magnesium alloy castings, machine faster than any other metal. Providing the geometry of the part allows, the limiting factor is the power and speed of the machine rather than the quality of the tool material. The power required per cubic centimetre of metal removed varies from 9 to 14 watts per minute depending on the operation.

SURFACE TREATMENT

All the normal chromating, anodising and finishing treatments are applicable.

CORROSION RESISTANCE

ASTM B117 Salt spray test

Corrosion rate 3.7mg/cm²/day
 285mpy

AMBIENT TEMPERATURE MECHANICAL PROPERTIES

TYPICAL TENSILE PROPERTIES

0.2% Proof stress 195 MPa
Tensile strength 261 MPa
Elongation 4%

TYPICAL COMPRESSIVE PROPERTIES

0.2% Proof stress 165-200 MPa
Ultimate strength 310-385 MPa

TYPICAL SHEAR PROPERTIES

Ultimate stress 152 MPa

TYPICAL SHEAR PROPERTIES

K_{IC} 16.4 MPa m^{1/2}

FATIGUE PROPERTIES

Rotating bend fatigue test

Endurance Limit MPa	Stress Reversals 5x10 ⁷
Unnotched	100 - 110
Notched	60 - 70

ELEKTRON[®] EQ2 I**ELEVATED TEMPERATURE
MECHANICAL PROPERTIES****TYPICAL TENSILE PROPERTIES**

	0.2% Proof stress (MPa)	Tensile strength (MPa)	Elongation (%)
100°C	189	230	10.0
150°C	180	211	16.0
200°C	170	191	16.0
250°C	152	169	15.0

CREEP STRENGTH

Stress (MPa) to produce specific creep strains

	Hours	0.1%	0.2%	0.3%
150°C	10	149	-	-
	100	138	155	-
	500	128	140	155
	1000	123	134	152
200°C	10	109	-	-
	100	78	95	116
	500	57	73	88
	1000	-	62	76
250°C	10	46	-	-
	100	29	36	42
	500	17	24	29
	1000	-	19	24

† The information contained within is meant as a guideline only

© Copyright Magnesium Elektron Ltd 2014. The information provided within this document is aimed to assist manufacturers and other interested parties in the use of magnesium alloys. Magnesium Elektron accepts no liability in whole or in part from use and interpretation of the data herein. All information is given in good faith but without warranty. Freedom from patent rights must not be assumed. Health and Safety information is available for all Magnesium Elektron products. MAGNESIUM ELEKTRON, The 'e' Logo, MEL, ELEKTRON and ZIRMAX are registered trademarks of Magnesium Elektron Limited.



Certificate No. FM12677

Magnesium Elektron UK
Magnesium Technology Centre,
Rake Lane, Swinton, Manchester
M27 8BF, England
Tel: +44 (0)161 911 1000

Magnesium Elektron Alloys
4601 Westown Parkway
Suite 130 West Des Moines
IA 50266, USA
Tel: +1 515 421 4100